

## BASF Aktiengesellschaft

December 3, 1997 NAE19960920US IB/SF/cd/ws7

## TOF YHE DISCUSURE

The laminated sheet or film comprises

- (1) a substrate layer comprising based on the sum of the amounts of components A and B and, if used, C and/or D, which totals 100% by weight 10
  - 1 99% by weight of a particular graft copolymer a as component A,
- 1 99% by weight of a copolymer of b 15
  - b1 40 - 100% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component B1,
- **b**2 up to 60% by weight of acrylonitrile or methacrylonitrile as 20 component B2,

as component B,

- 0 80% by weight of polycarbonates as component C, and 25 C
  - d 0 - 50% by weight of fibrous or particulate fillers or mixtures thereof as component D,

and

(3) a transparent top layer of polymethyl methacrylate.